

Comment on "Low to High Spin-state Transition Induced by charge ordering in Antiferromagnetic YBaCo₂O₅"

Z. Ropka

Center for Solid State Physics, S^{nt} Filip 5, 31-150 Kraków.

R.J. Radwanski

Center for Solid State Physics, S^{nt} Filip 5, 31-150 Kraków,

Institute of Physics, Pedagogical University, 30-084 Kraków, POLAND.

email: sfradwan@cyf-kr.edu.pl

In the commented Letter Vogt et al. (Phys.Rev.Lett. 84 (2000) 2969) claim the existence of a spin-state transition in YBaCo₂O₅. We think that this claim about the change from the low spin to high spin state upon cooling in YBaCo₂O₅ is erroneous.

Keywords: magnetism, 3d ions, low spin,

PRL submit: 31-07-2000

In Ref. 1 Vogt et al. claim the existence of a spin-state transition in YBaCo₂O₅. The spin state changes from low spin to high spin upon cooling. We think that this claim is erroneous. In Ref. 1 this claim has been derived on basis of

A) the comparison of the neutron-diffraction derived moment of $2.10 \mu_B$ per average cobalt ion at 300 K with the neutron-diffraction derived moment of $2.7 \mu_B$ and $4.2 \mu_B$ at 25 K. We will denote the magnetic moment derived by neutron-diffraction experiments by m_n .

B) a theoretical analysis of the value of $2.10 \mu_B$ found at 300 K as corresponding "to the spin-only value expected for a mixed valence compound containing equal concentrations of low spin (LS) Co²⁺ (${}^6t_{2g} {}^1e_g$, $S=1/2$, $\mu_{so} = 1.73 \mu_B$) and intermediate spin (IS) Co³⁺ (${}^5t_{2g} {}^1e_g$, $S=1$, $\mu_{so} = 2.85 \mu_B$)". Values of 2.7 and $4.2 \mu_B$ found at 25 K have been interpreted in Ref. 1 as related with "IS Co³⁺ (${}^5t_{2g} {}^1e_g$, $S=1$, $\mu_{so} = 2.85 \mu_B$) and HS (high spin) Co²⁺ (${}^5t_{2g} {}^2e_g$, $S=3/2$, $\mu_{so} = 3.87 \mu_B$)" or to an alternative composition of "HS Co³⁺ (${}^4t_{2g} {}^2e_g$,

$S=2$, $\mu_{so} = 4.89 \mu_B$) and HS Co^{2+} ($^5t_{2g}^2e_g$, $S=3/2$, $\mu_{so} = 3.87 \mu_B$)”.

According to us the behaviour described in point A is fully conventional for the ordered magnetic moment as is the case of YBaCo_2O_5 with T_N of 330 K - the ordered moment always increases with the decreasing temperature being zero above T_N [see, e.g. Ref. 2, ch.15 or Ref. 3 ch. 31]. Thus the claim about the change of the spin state from the low spin to high spin upon cooling is a misunderstanding. In the recalled by authors of Ref. 1 the case of LaCoO_3 there is a transition from a high to low-spin state (via an intermediate state) upon cooling [4,5], i.e. the moment at lower temperature is lower than at high temperatures what makes LaCoO_3 the intriguing case.

The theoretical analysis mentioned as point B is even more erroneous. The authors of the commented paper [1] erroneously compare the value of the ordered moment found in the neutron diffraction experiments m_n with the theoretical values for the effective moment observed in the paramagnetic state. The former is proportional to the z component of the quantum number S whereas the latter is related to the $\sqrt{S(S+1)}$. For the calculation of the magnetic moment we have to take into account $g_s=2$. It means that for the LS Co^{2+} ion described by $S=1/2$ one should expect the ordered moment of $1 \mu_B$ (m_n) whereas the effective moment p_{eff} of $1.73 \mu_B$ would be observed in the paramagnetic state in the temperature dependence of the paramagnetic susceptibility. Similarly for $S=1$ we have $m_n=2 \mu_B$ but $p_{eff} = 2.83$, for $S=3/2$ we have $m_n=3 \mu_B$ but $p_{eff} = 3.87$, for $S=2$ we have $m_n=4 \mu_B$ but $p_{eff} = 4.89 \mu_B$ [Ref. 2, ch. 14 Table 2, Ref. 3 ch. 31 Table 31.4]. The value given in Ref. 1 for $S=1$ is slightly wrong (2.85 instead of 2.83 μ_B). In such the situation, the explanation for the value of $2.10 \mu_B$ made in Ref. 1 is not valid any more. As well as for others.

In the above discussion we do not touch at all the problem of the orbital moment and the applicability of the spin-only theory to real 3d-ion systems. This orbital moment has to be taken into account in order to explain the ordered-moment value of $4.2 \mu_B$ as the spin-only theory yields the maximal value of $4 \mu_B$ for Co^{3+} and $3 \mu_B$ for the Co^{2+} ions. The moment of the needed value has been found recently for the atomic-like $3d^6$ systems, relevant to the Co^{3+} and Fe^{2+} ions, taking into account the spin-orbit coupling that enables revealing

of the orbital magnetic moment [6-8]. Moreover, in Ref. 6 the very large influence of the local symmetry on the local moment has been discussed showing that not always the largest z-component of the angular momentum is realized as the ground state what can lead to the non-magnetic ground state of the Co^{3+} ion in the high-spin state $S=2$ like it is in LaCoO_3 .

In conclusion, the claim of Ref. 1 about the change from the low spin to high spin state upon cooling in YBaCo_2O_5 is erroneous.

- [1] T.Vogt et al. Phys.Rev.Lett. 84, 2969 (2000).
- [2] C.Kittel, in: Introduction to Solid State Physics (1996), ch.14 and 15.
- [3] N.W.Aschroft and N.D.Mermin, in: Solid State Physics (1976) ch. 31.
- [4] M.A.Korotin et al. Phys.Rev. B 54, 5309 (1996).
- [5] P.Ravindran et al. Phys.Rev. B 60, 16423 (1999).
- [6] R.J.Radwanski and Z.Ropka, Solid State Commun. 112 (1999) 621.
- [7] R.J.Radwanski and Z.Ropka, Relativistic effects in the electronic structure for the 3d paramagnetic ions, <http://xxx.lanl.gov/abs/cond-mat/9907140>.
- [8] Z.Ropka, R.Michalski and R.J.Radwanski, Electronic and magnetic properties of FeBr_2 , <http://xxx.lanl.gov/abs/cond-mat/0005502>.